

TITLE OF THE INVENTION

Polymer, Resist Composition and Patterning Process

5 This invention relates to polymers suitable as the
base resin in chemically amplified positive resist
compositions used for micropatterning in a process for the
fabrication of semiconductor devices. It also relates to
chemically amplified positive resist compositions adapted
10 for exposure to high-energy radiation such as deep-UV, KrF
excimer laser light (248 nm), ArF excimer laser light (193
nm), electron beams or x-rays and a process for forming a
pattern.

BACKGROUND OF THE INVENTION

15 While a number of recent efforts are being made to
achieve a finer pattern rule in the drive for higher
integration and operating speeds in LSI devices, the
commonly used light exposure technology is approaching the
20 essential limit of resolution determined by the light source
wavelength. For the light exposure using g-line (436 nm) or
i-line (365 nm), a pattern rule of about 0.5 μ m is thought
to be the limit. The LSI fabricated using such light
25 exposure has a maximum degree of integration corresponding
to 16 M-bit dynamic random access memory (DRAM). However,
the laboratory fabrication of LSI already reached this stage,
and the development of a further micropatterning technology
is in urgent demand.

30 One means for reducing the pattern size is to reduce
the wavelength of exposure light used in forming a resist
pattern. For the mass production process of 256 M-bit DRAM
(processing size up to 0.25 μ m), it is now under intensive
consideration to replace i-line (365 nm) as the exposure
35 light source by KrF excimer laser light of a shorter
wavelength of 248 nm. However, for the fabrication of DRAM
with a degree of integration of 1 G or more requiring a

finer patterning technology (processing size up to 0.2 μm), a shorter wavelength light source is required, and in particular, photolithography using ArF excimer laser light (193 nm) is now under investigation.

5 Since H. Ito, G. C. Willson et al of IBM proposed a chemically amplified positive resist composition comprising a resin in the form of polyhydroxystyrene having hydroxyl groups blocked with tert-butoxycarbonyloxy (tBOC) groups, that is, poly(4-t-butoxycarbonyloxystyrene) (PBOCST) and a
10 photoacid generator in the form of an onium salt, a number of resist compositions having a high sensitivity and resolution have been developed. These chemically amplified positive resist compositions all have a high sensitivity and resolution, but are difficult to form fine patterns with a
15 high aspect ratio because the patterns' mechanical strength is low.

A number of chemically amplified positive resist compositions using the above-mentioned polyhydroxystyrene as the base resin and having sensitivity to deep-UV, electron
20 beams and x-rays are known in the art. These resist compositions, however, rely on the single-layer resist method although the bi-layer resist method is advantageous in forming a pattern with a high aspect ratio on a stepped substrate. These resist compositions are not yet
25 practically acceptable because of the outstanding problems of substrate steps, light reflection from substrates, and difficulty of forming high-aspect ratio patterns.

As is known in the art, the bi-layer resist method is advantageous in forming a high-aspect ratio pattern on a
30 stepped substrate. It is also known that in order to develop a bi-layer resist film with a common alkaline developer, high molecular weight silicone compounds having hydrophilic groups such as hydroxyl and carboxyl groups must be used.

35 Among silicone base chemically amplified positive resist compositions, recently proposed were those compositions comprising a base resin in the form of

polyhydroxybenzylsilsesquioxane, which is a stable alkali-soluble silicone polymer, in which some phenolic hydroxyl groups are blocked with tBOC groups, in combination with a photoacid generator (see JP-A 7-118651 and SPIE vol. 1925 (1993), 377). Also JP-A 9-110938 discloses a silicone-containing polymer using a silicon-containing acrylic monomer.

The silicon-containing polymer of the acrylic pendant type has the drawback that its resistance to dry etching with oxygen plasma is weak as compared with The silsesquioxane polymer. A low silicon content accounts for this weak dry etching resistance. The silicon-containing polymer of the siloxane pendant type has the drawback that it is repellent to developer and less wettable therewith. Then SPIE vol. 3678, pp. 214, 241 and 562 describes a polymer containing a monomer of the trisilane or tetrasilane pendant type having an increased silicon content and a silicon-containing substituent which can be eliminated with acid. However, since silane compounds of at least disilane exhibit strong absorption at the wavelength of ArF excimer laser, an increased introduction of such silanes undesirably leads to a lower transmittance. Besides, an attempt of introducing silicon into acid labile groups is reported in SPIE vol. 3678, p. 420. Because of a low acid elimination ability, there are drawbacks including low environmental stability and a T-top profile.


SUMMARY OF THE INVENTION

An object of the invention is to provide a novel polymer which is useful as the base polymer in a chemically amplified positive resist composition having a high sensitivity and high resolution, especially suitable as a material for use in the bi-layer resist method adapted to form a high-aspect ratio pattern, and capable of forming a pattern having improved heat resistance. Another object of the invention is to provide a chemically amplified positive

resist composition comprising the polymer as the base resin, and a method for forming a pattern using the same.

We have found that by incorporating silicon-containing substituent groups of the general formula (1) to be shown below, the silicon content of a polymer can be increased to an effective level to prevent the transmittance of ArF excimer laser light from lowering. The silicon-containing substituent group of formula (1) functions as an acid-eliminatable substituent group by substituting for the hydroxyl group on a carboxylic acid, alcohol or phenol, and especially the hydroxyl group of a phenol or carboxyl group as shown by the general formula (2) to (5) to be shown below. This substituent group has so high an acid eliminating ability that the environmental stability following exposure is improved and a T-top profile is thus precluded.


In a first aspect, the invention provides a polymer having silicon-containing groups of the general formula (1).




Herein R^1 to R^4 each are independently hydrogen or a straight, branched or cyclic alkyl group of 1 to 20 carbon atoms, or R^1 and R^2 , taken together, may form an aliphatic hydrocarbon ring in which $-\text{CH}_2-$ may be substituted with a $-\text{Si}(\text{R}^8)_2-$ group, and R^3 and R^4 , taken together, may form an aliphatic hydrocarbon ring in which $-\text{CH}_2-$ may be substituted with a $-\text{Si}(\text{R}^8)_2-$ group. R^5 to R^7 each are independently a straight, branched or cyclic alkyl or fluorinated alkyl group of 1 to 20 carbon atoms or aryl group of 6 to 20 carbon atoms. R^8 is independently a straight or branched alkyl group of 1 to 4 carbon atoms, and m is 1 or 2.

Preferably, hydrogen atoms of hydroxyl groups on a carboxylic acid, alcohol or phenol are substituted with the silicon-containing groups of the general formula (1).


A preferred embodiment of the invention provides a polymer comprising recurring units of one of the general formulae (2) to (5).




(2)



(3)



(4)



(5)

- 5 Herein R^1 to R^7 and m are as defined above. R^9 is hydrogen, a straight, branched or cyclic alkyl group of 1 to 20 carbon atoms, or $\text{CH}_2\text{CO}_2R^{12}$. R^{10} is hydrogen or a straight, branched or cyclic alkyl group of 1 to 20 carbon atoms. R^{11} is a straight, branched or cyclic alkylene group of 1 to 10 carbon atoms. R^{12} is hydrogen or a straight, branched or cyclic alkyl group of 1 to 20 carbon atoms, n is a number of 0 to 5, p is a number of 1 to 5, each of q and r is 0 or 1.

- 10 In a second aspect, the invention provides a chemically amplified positive resist composition comprising (A) the polymer defined above, (B) a photoacid generator, and (C) an organic solvent. Also contemplated herein is a chemically amplified positive resist composition comprising (A) the polymer defined above, (B) a photoacid generator, (C) an organic solvent, and (D) a dissolution rate inhibitor

having an acid labile group. The resist composition may further include (E) a basic compound.


In a third aspect, the invention provides a process for forming a pattern, comprising the steps of applying the positive resist composition onto an organic film on a substrate to form a coating; prebaking the coating to form a resist film; exposing the resist film in a pattern circuit region to radiation; post-exposure baking the resist film; developing the resist film with an aqueous alkaline solution to dissolve away the exposed area, thereby forming a resist pattern; and processing the organic film with an oxygen plasma generated by a dry etching apparatus.

DESCRIPTION OF THE PREFERRED EMBODIMENT

15 Polymer

Polymer

The polymer or high molecular weight compound of the invention contains silicon-containing groups of the following general formula (1).



Specifically, the inventive polymer has silicon-
containing acid labile groups which exert the β -cation
stabilizing effect of silicon substitution. These groups
advantageously have an improved acid elimination ability and
prevent the development of a T-top profile. Since silicon
atoms are separated by carbon atoms, the formation of a
disilane bond is precluded, eliminating the risk of lowering
the transmittance to ArF laser light.

In formula (1), R^1 to R^4 , which may be the same or different, are independently selected from hydrogen and straight, branched or cyclic alkyl groups of 1 to 20 carbon atoms, preferably 1 to 10 carbon atoms, and more preferably 1 to 6 carbon atoms. Examples of suitable straight, branched or cyclic alkyl groups include methyl, ethyl,


propyl, isopropyl, n-butyl, isobutyl, tert-butyl, pentyl, cyclopentyl, hexyl, octyl, decyl, and dodecyl.

Alternatively, a pair of R^1 and R^2 or a pair of R^3 and R^4 , taken together with the carbon atom to which they are


5 bonded, may form an aliphatic hydrocarbon ring having 4 to 20 carbon atoms, preferably 6 to 15 carbon atoms, and more preferably 6 to 10 carbon atoms. In this case, each of R^1 and R^2 or each of R^3 and R^4 may be a straight, branched or
10 cyclic alkylene group represented by $-(CH_2)_x-$ wherein x is selected so as to form an aliphatic hydrocarbon ring having a carbon number in the above range. Some or all of the $-CH_2-$ groups may be substituted with $-Si(R^8)_2-$ groups wherein R^8 is independently a straight or branched alkyl group of 1 to 4 carbon atoms.

15 R^5 to R^7 , which may be the same or different, are independently selected from straight, branched or cyclic alkyl or fluorinated alkyl groups of 1 to 20 carbon atoms, preferably 1 to 10 carbon atoms, and more preferably 1 to 6 carbon atoms, and aryl groups of 6 to 20 carbon atoms,
20 preferably 6 to 16 carbon atoms, and more preferably 6 to 12 carbon atoms. Exemplary alkyl groups are as enumerated above. Suitable fluorinated alkyl groups include the foregoing alkyl groups in which some or all of the hydrogen atoms are replaced by fluorine atoms, for example,
25 difluoromethyl, 2,2-difluoroethyl, 2,2,2-trifluoroethyl, 3,3,3-trifluoropropyl, 2,2,3,3-tetrafluoropropyl and 2,2,3,3,3-pentafluoropropyl. Examples of suitable aryl groups include phenyl, tolyl, xylyl and naphthyl. The letter m is 1 or 2.


30 Preferably, the silicon-containing groups of the general formula (1) are included as having substituted for hydrogen atoms of hydroxyl groups on a carboxylic acid, alcohol or phenol. In this regard, the polymer of the invention is preferably defined as comprising recurring
35 units of any one of the general formulae (2) to (5).




(2)



(3)



(4)




(5)


Herein R^1 to R^7 are as defined above; R^9 is hydrogen, a straight, branched or cyclic C_{1-20} alkyl group, or $CH_2CO_2R^{12}$; R^{10} is hydrogen or a straight, branched or cyclic C_{1-20} alkyl group; R^{11} is a straight, branched or cyclic C_{1-10} alkylene group; R^{12} is hydrogen or a straight, branched or cyclic C_{1-20} alkyl group; m is 1 or 2, n is a number of 0 to 5, p is a number of 1 to 5, each of q and r is 0 or 1.

Examples of the C_{1-20} alkyl group are as enumerated above, with those groups having 1 to 15 carbon atoms, especially 1 to 6 carbon atoms being preferred. Examples of C_{1-10} alkylene groups include methylene, ethylene, propylene, butylene, pentylene, cyclopentylene, hexylene, cyclohexylene and octylene, with those groups having 1 to 6 carbon atoms, especially 1 to 3 carbon atoms being preferred.


Illustrative examples of the recurring units having silicon-containing acid labile groups of formulae (2) through (5) are given below. It is noted that Me is methyl and Et is ethyl.




The silicon-containing polymer of the invention, which includes recurring units having silicon-containing substituent groups of acid-eliminatable nature, may further include additional recurring units having acid-eliminatable substituent groups for the purpose of enhancing the contrast. Like the silicon-containing acid-eliminatable substituent groups, these groups are preferably incorporated as having substituted for hydrogen atoms of hydroxyl groups on a carboxylic acid, alcohol or phenol. Thus the additional recurring units are preferably any one of the following units.




(2A)



(3A)





(4A)



(5A)

Herein R^e is an acid-eliminatable substituent group, R^9 , R^{10} , R^{11} , n and r are as defined above.


The acid-eliminatable substituent groups, also referred to as acid labile groups, may be selected from a variety of such groups, and preferably from among groups of the following formulae (26) and (27), tertiary C_{4-40} alkyl groups of the following formula (28), and oxoalkyl groups of 4 to 20 carbon atoms.




In formula (26), R^{13} is a tertiary alkyl group of 4 to 20 carbon atoms, preferably 4 to 15 carbon atoms, an oxoalkyl group of 4 to 20 carbon atoms, or a group of formula (28). Exemplary tertiary alkyl groups are tert-butyl, tert-amyl, 1,1-diethylpropyl, 1-ethylcyclopentyl, 1-butylcyclopentyl, 1-ethylcyclohexyl, 1-butylcyclohexyl, 1-ethyl-2-cyclopentenyl, 1-ethyl-2-cyclohexenyl, and 2-methyl-2-adamantyl. Exemplary oxoalkyl groups are 3-oxocyclohexyl, 4-methyl-2-oxooxan-4-yl, and 5-methyl-5-oxooxolan-4-yl.

Letter "a" is an integer of 0 to 6.


In formula (27), R^{14} and R^{15} are hydrogen or straight, branched or cyclic alkyl groups of 1 to 18 carbon atoms, preferably 1 to 10 carbon atoms. Exemplary alkyl groups include methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl, cyclopentyl, cyclohexyl, 2-ethylhexyl, and n-octyl. R^{16} is a monovalent hydrocarbon group of 1 to 18 carbon atoms, preferably 1 to 10 carbon atoms, which may contain a hetero atom such as oxygen, examples of which include unsubstituted straight, branched or cyclic alkyl groups and straight, branched or cyclic alkyl groups in which some hydrogen atoms are replaced by hydroxyl, alkoxy, oxo, amino, alkylamino or the like. Illustrative examples are the substituted alkyl groups shown below.




(29)




(30)




(31)



(32)



(33)










(34)

A pair of R^{14} and R^{15} , R^{14} and R^{16} , or R^{15} and R^{16} may form a ring. Each of R^{14} , R^{15} and R^{16} is a straight or branched alkylene group of 1 to 18 carbon atoms, preferably 1 to 10 carbon atoms when they form a ring.

Examples of the acid labile groups of formula (26) include tert-butoxycarbonyl, tert-butoxycarbonylmethyl,

tert-amylloxycarbonyl, tert-amylloxycarbonylmethyl, 1,1-diethylpropyloxycarbonyl, 1,1-diethylpropyloxycarbonylmethyl, 1-ethylcyclopentyloxycarbonyl, 1-ethylcyclopentyl-oxycarbonylmethyl, 1-ethyl-2-cyclopentenylloxycarbonyl, 1-ethyl-2-cyclopentenylloxycarbonylmethyl, 1-ethoxyethoxy-carbonylmethyl, 2-tetrahydropyranyloxycarbonylmethyl, and 2-tetrahydrofuranyloxycarbonylmethyl groups.

Of the acid labile groups of formula (27), the straight and branched ones are exemplified by the following groups.




Of the acid labile groups of formula (27), the cyclic ones are, for example, tetrahydrofuran-2-yl, 2-methyltetrahydrofuran-2-yl, tetrahydropyran-2-yl, and 2-methyltetrahydropyran-2-yl. Preferred among the groups of formula (27) are ethoxyethyl, butoxyethyl and ethoxypropyl.

In formula (28), R^{17} , R^{18} and R^{19} are independently monovalent hydrocarbon groups, for example, straight, branched or cyclic alkyl groups of 1 to 20 carbon atoms, which may contain a hetero atom such as oxygen, sulfur, nitrogen or fluorine. A pair of R^{17} and R^{18} , a pair of R^{17} and R^{19} , or a pair of R^{18} and R^{19} , taken together, may form a ring.

Examples of the tertiary alkyl group represented by formula (28) include tert-butyl, triethylcarbyl, 1-ethylnorbornyl, 1-methylcyclohexyl, 1-ethylcyclopentyl, 2-(2-methyl)adamantyl, 2-(2-ethyl)adamantyl, and tert-amyl.


Other illustrative examples of the tertiary alkyl group are given below as formulae (35) through (50).




Herein, R^{20} and R^{21} each are a straight, branched or cyclic alkyl group of 1 to 6 carbon atoms, for example, methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, n-pentyl, n-hexyl, cyclopropyl, cyclopropylmethyl, cyclobutyl, cyclopentyl or cyclohexyl. R^{22} is hydrogen, a monovalent C_{1-6} hydrocarbon group which may contain a hetero atom or a monovalent C_{1-6} hydrocarbon group which may be separated by a hetero atom, with the hydrocarbon being typically alkyl. The hetero atom is an oxygen, sulfur or nitrogen atom, which is contained or intervenes in the form of -OH, -OR, -O-, -S-, -S(=O)-, -NH₂, -NHR, -NR₂, -NH-, or -NR- wherein R is an alkyl group of 1 to 20 carbon atoms, and especially 1 to 16 carbon atoms.

R^{23} is hydrogen or an alkyl, hydroxyalkyl, alkoxy or alkoxyalkyl group of 1 to 20 carbon atoms, especially 1 to 16 carbon atoms, which may be straight, branched or cyclic. Illustrative examples include methyl, hydroxymethyl, ethyl, hydroxyethyl, propyl, isopropyl, n-butyl, sec-butyl, n-pentyl, n-hexyl, methoxy, methoxymethoxy, ethoxy, and tert-butoxy.

The oxoalkyl groups of 4 to 20 carbon atoms include 3-oxocyclohexyl and groups of the following formulae.




For improving adhesion, the polymer may additionally include recurring units of at least one type containing a hydrophilic substituent group such as anhydride, ester (lactone), carbonate, alcohol, amide or ketone, which units are enumerated below.




Herein R^9 and R^{10} are as defined above.


In the polymer, further recurring units can be incorporated for the purpose of increasing the silicon content of the polymer to enhance its resistance to oxygen plasma etching. Examples of further recurring units are given below.




(Si-1)




(Si-2)



(Si-3)



(Si-4)




(Si-5)

Herein R^9 is as defined above and Me is methyl.

The polymer is prepared in a conventional manner by furnishing predetermined amounts of a monomer having a silicon-containing group of formula (1), preferably a monomer or monomers capable of forming units of the formulae (2) through (5) and optionally, a monomer or monomers capable of forming units of formulae (2A) to (5A), a monomer or monomers capable of forming units of formulae (53) to (90) and a monomer or monomers capable of forming units of formulae (Si-1) to (Si-5), mixing the monomers in a solvent,

adding a catalyst, and effecting polymerization reaction while heating or cooling if necessary. The polymerization reaction depends on the type of initiator (or catalyst), trigger means (light, heat, radiation or plasma), and polymerization conditions (including temperature, pressure, concentration, solvent and additive). Commonly used for the preparation of the inventive polymer are a radical copolymerization mode utilizing a radical of 2,2'-azobisisobutyronitrile (AIBN) etc. for initiating polymerization and an ionic polymerization (anionic polymerization) mode using alkyl lithium catalysts. In either mode, polymerization can be done in a conventional manner. It is understood that the monomers capable of forming units of formulae (2) to (5) can be synthesized by the procedure described in Synthesis Example 1 or analogous procedures.

The polymer of the invention can be represented by the following formula.



Herein U^1 stands for recurring units having a silicon-containing group of formula (1), preferably recurring units of formulae (2) to (5), and especially recurring units of formulae (6) to (25); U^2 stands for recurring units of formulae (2A) to (5A); U^3 stands for recurring units of formulae (53) to (90); and U^4 stands for recurring units of formulae (Si-1) to (Si-5). The letters "a" to "d" are numbers satisfying $0 < a \leq 1$, $0 \leq b < 1$, $0 \leq c < 1$, $0 \leq d < 1$, and $a+b+c+d = 1$. Preferably "a" is from more than 0 to 0.9, more preferably from 0.2 to 0.8, "b" is from 0 to 0.5, more preferably from 0 to 0.3, "c" is from 0 to 0.8, more preferably from 0.1 to 0.6, and "d" is from 0 to 0.5, more preferably from 0 to 0.3.

The polymer preferably has a weight average molecular weight of about 1,000 to about 500,000, and especially about 3,000 to about 100,000.

Resist composition

The polymer of the invention is suitable as a base resin in a resist composition. Thus the invention provides a resist composition comprising the above-described polymer.

5 More specifically, the resist composition is defined herein as comprising (A) the above-described polymer as a base resin, (B) a photoacid generator, (C) an organic solvent, and optionally (D) a dissolution rate inhibitor having an acid labile group, (E) a basic compound and other
10 components.

Organic solvent (C)


The organic solvent used herein may be any organic solvent in which the base resin (the inventive polymer), photoacid generator, dissolution rate inhibitor and other
15 components are soluble. Illustrative, non-limiting, examples of the organic solvent include ketones such as cyclohexanone and methyl-2-n-amylketone; alcohols such as 3-methoxybutanol, 3-methyl-3-methoxybutanol, 1-methoxy-2-propanol, and 1-ethoxy-2-propanol; ethers such as propylene glycol monomethyl ether, ethylene glycol monomethyl ether,
20 propylene glycol monoethyl ether, ethylene glycol monoethyl ether, propylene glycol dimethyl ether, and diethylene glycol dimethyl ether; and esters such as propylene glycol monomethyl ether acetate, propylene glycol monoethyl ether acetate, ethyl lactate, ethyl pyruvate, butyl acetate,
25 methyl 3-methoxypropionate, ethyl 3-ethoxypropionate, tert-butyl acetate, tert-butyl propionate, and propylene glycol mono-tert-butyl ether acetate. These solvents may be used alone or in combinations of two or more thereof. Of the
30 above organic solvents, it is recommended to use diethylene glycol dimethyl ether, 1-ethoxy-2-propanol and ethyl lactate because the photoacid generator is most soluble therein, propylene glycol monomethyl ether acetate because it is a safe solvent, or a mixture thereof.

Photoacid generator (B)

35 Suitable examples of the photoacid generator (B) include onium salts of formula (91) below, diazomethane

derivatives of formula (92) below, glyoxime derivatives of formula (93) below, β -ketosulfone derivatives, disulfone derivatives, nitrobenzylsulfonate derivatives, sulfonic acid ester derivatives, and imidoyl sulfonate derivatives.

5




(91)

In the formula, R^{24} is a straight, branched or cyclic alkyl of 1 to 12 carbon atoms, an aryl of 6 to 12 carbon atoms, or an aralkyl of 7 to 12 carbon atoms; M^+ is iodonium or sulfonium; K^- is a non-nucleophilic counter-ion; and the letter b is 2 or 3.

Illustrative examples of alkyl groups represented by R^{24} include methyl, ethyl, propyl, butyl, cyclohexyl, 2-oxocyclohexyl, norbornyl, and adamantyl. Exemplary aryl groups include phenyl; alkoxyphenyl groups such as p-methoxyphenyl, m-methoxyphenyl, o-methoxyphenyl, ethoxyphenyl, p-tert-butoxyphenyl, and m-tert-butoxyphenyl; and alkylphenyl groups such as 2-methylphenyl, 3-methylphenyl, 4-methylphenyl, ethylphenyl, 4-tert-butylphenyl, 4-butylphenyl, and dimethylphenyl. Exemplary aralkyl groups include benzyl and phenethyl. Examples of the non-nucleophilic counter-ion represented by K^- include halide ions such as chloride and bromide; fluoroalkylsulfonate ions such as triflate, 1,1,1-trifluoroethanesulfonate, and nonafluorobutanesulfonate; arylsulfonate ions such as tosylate, benzenesulfonate, 4-fluorobenzenesulfonate, and 1,2,3,4,5-pentafluorobenzenesulfonate; and alkylsulfonate ions such as mesylate and butanesulfonate.

25



(92)


30

In the formula, R^{25} and R^{26} are straight, branched or cyclic alkyl or halogenated alkyl groups of 1 to 12 carbon atoms, aryl or halogenated aryl groups of 6 to 12 carbon atoms, or aralkyl groups of 7 to 12 carbon atoms.

35

Illustrative examples of alkyl groups represented by R^{25} and R^{26} include methyl, ethyl, propyl, butyl, amyl,

cyclopentyl, cyclohexyl, norbornyl, and adamantyl. Exemplary halogenated alkyl groups include trifluoromethyl, 1,1,1-trifluoroethyl, 1,1,1-trichloroethyl, and nonafluorobutyl. Exemplary aryl groups include phenyl; alkoxyphenyl groups such as p-methoxyphenyl, m-methoxyphenyl, o-methoxyphenyl, ethoxyphenyl, p-tert-butoxyphenyl, and m-tert-butoxyphenyl; and alkylphenyl groups such as 2-methylphenyl, 3-methylphenyl, 4-methylphenyl, ethylphenyl, 4-tert-butylphenyl, 4-butylphenyl, and dimethylphenyl. Exemplary halogenated aryl groups include fluorobenzene, chlorobenzene, and 1,2,3,4,5-pentafluorobenzene. Exemplary aralkyl groups include benzyl and phenethyl.



In the formula, R^{27} , R^{28} , and R^{29} are straight, branched or cyclic alkyl or halogenated alkyl groups of 1 to 12 carbon atoms, aryl or halogenated aryl groups of 6 to 12 carbon atoms, or aralkyl groups of 7 to 12 carbon atoms. R^{28} and R^{29} may together form a cyclic structure with the proviso that if they form a cyclic structure, each is a straight or branched alkylene group of 1 to 6 carbon atoms.

The alkyl, halogenated alkyl, aryl, halogenated aryl, and aralkyl groups represented by R^{27} , R^{28} , and R^{29} are exemplified by the same groups mentioned above for R^{25} and R^{26} . Examples of alkylene groups represented by R^{28} and R^{29} include methylene, ethylene, propylene, butylene, and hexylene.

Illustrative examples of the photoacid generator include:

onium salts such as diphenyliodonium trifluoromethanesulfonate, (p-tert-butoxyphenyl)phenyliodonium trifluoromethanesulfonate, diphenyliodonium p-toluenesulfonate, (p-tert-butoxyphenyl)phenyliodonium p-toluenesulfonate, triphenylsulfonium trifluoromethanesulfonate, (p-tert-butoxyphenyl)diphenylsulfonium trifluoromethanesulfonate, bis(p-tert-butoxyphenyl)phenylsulfonium trifluoromethanesulfonate, tris(p-tert-butoxyphenyl)sulfonium trifluoro-

methanesulfonate, triphenylsulfonium p-toluenesulfonate, (p-tert-butoxyphenyl)diphenylsulfonium p-toluenesulfonate, bis(p-tert-butoxyphenyl)phenylsulfonium p-toluenesulfonate, tris(p-tert-butoxyphenyl)sulfonium p-toluenesulfonate, 5 triphenylsulfonium nonafluorobutanesulfonate, triphenylsulfonium butanesulfonate, trimethylsulfonium trifluoromethanesulfonate, trimethylsulfonium p-toluenesulfonate, cyclohexylmethyl(2-oxocyclohexyl)sulfonium trifluoromethanesulfonate, cyclohexylmethyl(2-oxocyclohexyl)sulfonium p-10 toluenesulfonate, dimethylphenylsulfonium trifluoromethanesulfonate, dimethylphenylsulfonium p-toluenesulfonate, dicyclohexylphenylsulfonium trifluoromethanesulfonate, and dicyclohexylphenylsulfonium p-toluenesulfonate;

diazomethane derivatives such as bis(benzenesulfonyl)-15 diazomethane, bis(p-toluenesulfonyl)diazomethane, bis(xylenesulfonyl)diazomethane, bis(cyclohexylsulfonyl)diazomethane, bis(cyclopentylsulfonyl)diazomethane, bis(n-butylsulfonyl)diazomethane, bis(isobutylsulfonyl)diazomethane, bis(sec-butylsulfonyl)diazomethane, bis(n-propylsulfonyl)diazomethane, bis(isopropylsulfonyl)diazomethane, 20 bis(tert-butylsulfonyl)diazomethane, bis(n-amylsulfonyl)diazomethane, bis(isoamylsulfonyl)diazomethane, bis(sec-amylsulfonyl)diazomethane, bis(tert-amylsulfonyl)diazomethane, 1-cyclohexylsulfonyl-1-(tert-butylsulfonyl)diazomethane, 1-cyclohexylsulfonyl-1-(tert-amylsulfonyl)diazomethane, 25 and 1-tert-amylsulfonyl-1-(tert-butylsulfonyl)diazomethane;

glyoxime derivatives such as bis-O-(p-toluene-sulfonyl)-α-dimethylglyoxime, bis-O-(p-toluenesulfonyl)-α-30 diphenylglyoxime, bis-O-(p-toluenesulfonyl)-α-dicyclohexylglyoxime, bis-O-(p-toluenesulfonyl)-2,3-pentanedione-glyoxime, bis-O-(p-toluenesulfonyl)-2-methyl-3,4-pentanedione-glyoxime, bis-O-(n-butanefulfonyl)-α-dimethylglyoxime, bis-O-(n-butanesulfonyl)-α-diphenylglyoxime, bis-O-(n-butane-35 sulfonyl)-α-dicyclohexylglyoxime, bis-O-(n-butanefulfonyl)-2,3-pentanedione-glyoxime, bis-O-(n-butanefulfonyl)-2-methyl-

3,4-pentanedione glyoxime, bis-O-(methanesulfonyl)- α -dimethylglyoxime, bis-O-(trifluoromethanesulfonyl)- α -dimethylglyoxime, bis-O-(1,1,1-trifluoroethanesulfonyl)- α -dimethylglyoxime, bis-O-(tert-buthanesulfonyl)- α -dimethylglyoxime, bis-O-(perfluorooctanesulfonyl)- α -dimethylglyoxime, bis-O-(cyclohexanesulfonyl)- α -dimethylglyoxime, bis-O-(benzenesulfonyl)- α -dimethylglyoxime, bis-O-(p-fluorobenzenesulfonyl)- α -dimethylglyoxime, bis-O-(p-tert-butylbenzenesulfonyl)- α -dimethylglyoxime, bis-O-(xylenesulfonyl)- α -dimethylglyoxime, and bis-O-(camphorsulfonyl)- α -dimethylglyoxime;

β -ketosulfone derivatives such as 2-cyclohexyl-carbonyl-2-(p-toluenesulfonyl)propane and 2-isopropyl-carbonyl-2-(p-toluenesulfonyl)propane;

disulfone derivatives such as diphenyl disulfone and dicyclohexyl disulfone;

nitrobenzyl sulfonate derivatives such as 2,6-dinitrobenzyl p-toluenesulfonate and 2,4-dinitrobenzyl p-toluenesulfonate;

sulfonic acid ester derivatives such as 1,2,3-tris(methanesulfonyloxy)benzene, 1,2,3-tris(trifluoromethanesulfonyloxy)benzene, and 1,2,3-tris(p-toluenesulfonyloxy)benzene; and

imidoyl sulfonate derivatives such as phthalimidoyl triflate, phthalimidoyl tosylate, 5-norbornene-2,3-dicarboxyimidoyl triflate, 5-norbornene-2,3-dicarboxyimidoyl tosylate, and 5-norbornene-2,3-dicarboxyimidoyl n-butylsulfonate.

Preferred among these photoacid generators are onium salts such as triphenylsulfonium trifluoromethanesulfonate, (p-tert-butoxyphenyl)diphenylsulfonium trifluoromethanesulfonate, tris(p-tert-butoxyphenyl)sulfonium trifluoromethanesulfonate, triphenylsulfonium p-toluenesulfonate, (p-tert-butoxyphenyl)diphenylsulfonium p-toluenesulfonate, and

tris(p-tert-butoxyphenyl)sulfonium p-toluenesulfonate;
diazomethane derivatives such as bis(benzenesulfonyl)diazomethane, bis(p-toluenesulfonyl)diazomethane, bis(cyclohexylsulfonyl)diazomethane, bis(n-butylsulfonyl)diazomethane,
5 bis(isobutylsulfonyl)diazomethane, bis(sec-butylsulfonyl)diazomethane, bis(n-propylsulfonyl)diazomethane, bis(isopropylsulfonyl)diazomethane, and bis(tert-butylsulfonyl)diazomethane; and glyoxime derivatives such as bis-O-(p-toluenesulfonyl)- α -dimethylglyoxime and bis-O-(n-
10 butanesulfonyl)- α -dimethylglyoxime. These photoacid generators may be used singly or in combinations of two or more thereof. Onium salts are effective for improving rectangularity, while diazomethane derivatives and glyoxime derivatives are effective for reducing standing waves. The
15 combination of an onium salt with a diazomethane or a glyoxime derivative allows for fine adjustment of the profile.

The photoacid generator is added in an amount of 0.2 to 15 parts by weight, and especially 0.5 to 8 parts by weight, per 100 parts by weight of all the base resins. At
20 less than 0.2 part, the amount of acid generated during exposure would be too low and the sensitivity and resolution are poor, whereas the addition of more than 15 parts would lower the transmittance of the resist and results in a poor
25 resolution.


Dissolution rate inhibitor (D)

To the resist composition, a dissolution rate inhibitor may be added. The dissolution rate inhibitor is a compound having on the molecule at least two phenolic
30 hydroxyl groups, in which an average of from 0 to 100 mol% of all the hydrogen atoms on the phenolic hydroxyl groups are replaced with acid labile groups or a compound having on the molecule at least one carboxyl group, in which an
average of 10 to 100 mol% of all the hydrogen atoms on the
35 carboxyl groups are replaced with silicon-containing groups of formula (1), both the compounds having an average


molecular weight within a range of 100 to 1,000, and preferably 150 to 800.

The degree of substitution of the hydrogen atoms on the phenolic hydroxyl groups with acid labile groups is on average at least 0 mol%, and preferably at least 30 mol%, of all the phenolic hydroxyl groups. The upper limit is 100 mol%, and preferably 80 mol%. The degree of substitution of the hydrogen atoms on the carboxyl groups with acid labile groups is on average at least 50 mol%, and preferably at least 70 mol%, of all the carboxyl groups, with the upper limit being 100 mol%.


Preferable examples of such compounds having two or more phenolic hydroxyl groups or compounds having at least one carboxyl group include those of formulas (D1) to (D14) below.




(D1)




(D2)




(D3)




(D4)




(D5)




(D6)




(D7)




(D8)




(D9)




(D10)




(D11)



(D12)



(D13)



(D14)

In these formulas, R^{101} and R^{102} are each hydrogen or a straight or branched alkyl or alkenyl of 1 to 8 carbon atoms; R^{103} is hydrogen, a straight or branched alkyl or alkenyl of 1 to 8 carbon atoms, or $-(R^{107})_h-COOH$; R^{104} is $-(CH_2)_i-$ (where $i = 2$ to 10), an arylene of 6 to 10 carbon atoms, carbonyl, sulfonyl, an oxygen atom, or a sulfur atom; R^{105} is an alkylene of 1 to 10 carbon atoms, an arylene of 6 to 10 carbon atoms, carbonyl, sulfonyl, an oxygen atom, or a sulfur atom; R^{106} is hydrogen, a straight or branched alkyl or alkenyl of 1 to 8 carbon atoms, or a hydroxyl-substituted phenyl or naphthyl; R^{107} is a straight or branched alkylene of 1 to 10 carbon atoms; R^{108} is hydrogen or hydroxyl; the letter j is an integer from 0 to 5; u and h are each 0 or 1; $s_1, t_1, s_2, t_2, s_3,$ and t_3 are each numbers which satisfy $s_1+t_1 = 8$, $s_2+t_2 = 5$, and $s_3+t_3 = 4$, and are such that each phenyl skeleton has at least one hydroxyl group; and α is a number such that the compounds of formula (D8) or (D9) have a molecular weight of from 100 to 1,000.

In the above formulas, suitable examples of R^{101} and R^{102} include hydrogen, methyl, ethyl, butyl, propyl, ethynyl, and cyclohexyl; suitable examples of R^{103} include the same groups as for R^{101} and R^{102} , as well as $-COOH$ and $-CH_2COOH$; suitable examples of R^{104} include ethylene, phenylene,

carbonyl, sulfonyl, oxygen, and sulfur; suitable examples of R^{105} include methylene as well as the same groups as for R^{104} ; and suitable examples of R^{106} include hydrogen, methyl, ethyl, butyl, propyl, ethynyl, cyclohexyl, and hydroxyl-substituted phenyl or naphthyl.

Basic compound (E)

The basic compound (E) is preferably a compound capable of suppressing the rate of diffusion when the acid generated by the photoacid generator diffuses within the resist film. The inclusion of this type of basic compound holds down the rate of acid diffusion within the resist film, resulting in better resolution. In addition, it suppresses changes in sensitivity following exposure, thus reducing substrate and environment dependence, as well as improving the exposure latitude and the pattern profile. (See, for example, JP-A 5-232706, JP-A 5-249683, JP-A 5-158239, JP-A 5-249662, JP-A 5-257282, JP-A 5-289322, and JP-A 5-289340).

Examples of suitable basic compounds include primary, secondary, and tertiary aliphatic amines, mixed amines, aromatic amines, heterocyclic amines, carboxyl group-bearing nitrogenous compounds, sulfonyl group-bearing nitrogenous compounds, hydroxyl group-bearing nitrogenous compounds, hydroxyphenyl group-bearing nitrogenous compounds, alcoholic nitrogenous compounds, amide derivatives, and imide derivatives. Of these, aliphatic amines are especially preferred.

Examples of suitable primary aliphatic amines include ammonia, methylamine, ethylamine, n-propylamine, isopropylamine, n-butylamine, iso-butylamine, sec-butylamine, tert-butylamine, pentylamine, tert-amylamine, cyclopentylamine, hexylamine, cyclohexylamine, heptylamine, octylamine, nonylamine, decylamine, dodecylamine, cetylamine, methylenediamine, ethylenediamine, and tetraethylenepentamine. Examples of suitable secondary aliphatic amines include dimethylamine, diethylamine, di-n-propylamine, di-iso-propylamine, di-n-butylamine, di-iso-butylamine, di-sec-butylamine, dipentylamine, dicyclopentylamine, dihexylamine,

dicyclohexylamine, diheptylamine, dioctylamine, dinonylamine, didecylamine, didodecylamine, dicetylamine, N,N-dimethylmethylenediamine, N,N-dimethylethylenediamine, and N,N-dimethyltetraethylenepentamine. Examples of suitable tertiary aliphatic amines include trimethylamine, triethylamine, tri-n-propylamine, tri-iso-propylamine, tri-n-butylamine, tri-iso-butylamine, tri-sec-butylamine, tripentylamine, tricyclopentylamine, trihexylamine, tricyclohexylamine, triheptylamine, trioctylamine, trinonylamine, tridecylamine, tridodecylamine, tricetylamine, N,N,N',N'-tetramethylmethylenediamine, N,N,N',N'-tetramethylethylenediamine, and N,N,N',N'-tetramethyltetraethylenepentamine.



Examples of suitable mixed amines include dimethylethylamine, methylethylpropylamine, benzylamine, phenethylamine, and benzyldimethylamine. Examples of suitable aromatic and heterocyclic amines include aniline derivatives (e.g., aniline, N-methylaniline, N-ethylaniline, N-propylaniline, N,N-dimethylaniline, 2-methylaniline, 3-methylaniline, 4-methylaniline, ethylaniline, propylaniline, trimethylaniline, 2-nitroaniline, 3-nitroaniline, 4-nitroaniline, 2,4-dinitroaniline, 2,6-dinitroaniline, 3,5-dinitroaniline, and N,N-dimethyltoluidine), diphenyl(p-tolyl)amine, methyldiphenylamine, triphenylamine, phenylenediamine, naphthylamine, diaminonaphthalene, pyrrole derivatives (e.g., pyrrole, 2H-pyrrole, 1-methylpyrrole, 2,4-dimethylpyrrole, 2,5-dimethylpyrrole, and N-methylpyrrole), oxazole derivatives (e.g., oxazole and isooxazole), thiazole derivatives (e.g., thiazole and isothiazole), imidazole derivatives (e.g., imidazole, 4-methylimidazole, and 4-methyl-2-phenylimidazole), pyrazole derivatives, furazan derivatives, pyrroline derivatives (e.g., pyrroline and 2-methyl-1-pyrroline), pyrrolidine derivatives (e.g., pyrrolidine, N-methylpyrrolidine, pyrrolidinone, and N-methylpyrrolidone), imidazoline derivatives, imidazolidine derivatives, pyridine derivatives (e.g., pyridine, methylpyridine, ethylpyridine, propylpyridine, butylpyridine, 4-(1-butylpentyl)pyridine, dimethylpyridine, trimethylpyridine,

triethylpyridine, phenylpyridine, 3-methyl-2-phenylpyridine,
4-tert-butylpyridine, diphenylpyridine, benzylpyridine,
methoxypyridine, butoxypyridine, dimethoxypyridine, 1-
methyl-2-pyridine, 4-pyrrolidinopyridine, 1-methyl-4-phenyl-
5 pyridine, 2-(1-ethylpropyl)pyridine, aminopyridine, and
dimethylaminopyridine), pyridazine derivatives, pyrimidine
derivatives, pyrazine derivatives, pyrazoline derivatives,
pyrazolidine derivatives, piperidine derivatives, piperazine
derivatives, morpholine derivatives, indole derivatives,
10 isoindole derivatives, 1H-indazole derivatives, indoline
derivatives, quinoline derivatives (e.g., quinoline and 3-
quinolinecarbonitrile), isoquinoline derivatives, cinnoline
derivatives, quinazoline derivatives, quinoxaline
derivatives, phthalazine derivatives, purine derivatives,
15 pteridine derivatives, carbazole derivatives, phenanthridine
derivatives, acridine derivatives, phenazine derivatives,
1,10-phenanthroline derivatives, adenine derivatives,
adenosine derivatives, guanine derivatives, guanosine
derivatives, uracil derivatives, and uridine derivatives.

20 Examples of suitable carboxyl group-bearing
nitrogenous compounds include aminobenzoic acid, indole-
carboxylic acid, and amino acid derivatives (e.g. nicotinic
acid, alanine, arginine, aspartic acid, glutamic acid,
glycine, histidine, isoleucine, glycylleucine, leucine,
25 methionine, phenylalanine, threonine, lysine, 3-amino-
pyrazine-2-carboxylic acid, and methoxyalanine). Examples
of suitable sulfonyl group-bearing nitrogenous compounds
include 3-pyridinesulfonic acid and pyridinium p-toluene-
sulfonate. Examples of suitable hydroxyl group-bearing
30 nitrogenous compounds, hydroxyphenyl group-bearing
nitrogenous compounds, and alcoholic nitrogenous compounds
include 2-hydroxypyridine, aminocresol, 2,4-quinolinediol,
3-indolemethanol hydrate, monoethanolamine, diethanolamine,
triethanolamine, N-ethyldiethanolamine, N,N-diethylethanol-
35 amine, triisopropanolamine, 2,2'-iminodiethanol, 2-amino-
ethanol, 3-amino-1-propanol, 4-amino-1-butanol, 4-(2-
hydroxyethyl)morpholine, 2-(2-hydroxyethyl)pyridine, 1-(2-

hydroxyethyl)piperazine, 1-[2-(2-hydroxyethoxy)ethyl]-
 piperazine, piperidine ethanol, 1-(2-hydroxyethyl)-
 pyrrolidine, 1-(2-hydroxyethyl)-2-pyrrolidinone, 3-
 piperidino-1,2-propanediol, 3-pyrrolidino-1,2-propanediol,
 5 8-hydroxyjulolidine, 3-quinuclidinol, 3-tropanol, 1-methyl-
 2-pyrrolidine ethanol, 1-aziridine ethanol, N-(2-hydroxy-
 ethyl)phthalimide, and N-(2-hydroxyethyl)isonicotinamide.
 Examples of suitable amide derivatives include formamide, N-
 methylformamide, N,N-dimethylformamide, acetamide, N-methyl-
 10 acetamide, N,N-dimethylacetamide, propionamide, and
 benzamide. Suitable imide derivatives include phthalimide,
 succinimide, and maleimide.

In addition, basic compounds of the following general
 formulas (94) and (95) may also be included.



15

In the formulas, R^{201} , R^{202} , R^{203} , R^{207} and R^{208} are
 independently straight, branched or cyclic alkyls of 1 to
 20 carbon atoms; R^{204} , R^{205} , R^{206} , R^{209} and R^{210} are hydrogen,
 alkyls of 1 to 20 carbon atoms, or amino; R^{204} and R^{205} , R^{205}
 20 and R^{206} , R^{204} and R^{206} , R^{204} with R^{205} and R^{206} , and R^{209} and R^{210}
 may bond together to form rings; and X, Y and Z are each
 integers from 0 to 20, with the proviso that hydrogen is
 excluded from R^{204} , R^{205} , R^{206} , R^{209} and R^{210} when X, Y and Z are
 equal to 0.

25

The alkylene groups represented by R^{201} , R^{202} , R^{203} , R^{207}
 and R^{208} preferably have 1 to 20 carbon atoms, more
 preferably 1 to 10 carbon atoms, and most preferably 1 to 8

carbon atoms. Examples include methylene, ethylene, n-propylene, isopropylene, n-butylene, isobutylene, n-pentylene, isopentylene, hexylene, nonylene, decylene, cyclopentylene, and cyclohexylene.

5 The alkyl groups represented by R^{204} , R^{205} , R^{206} , R^{209} and R^{210} preferably have 1 to 20 carbon atoms, more preferably 1 to 8 carbon atoms, and most preferably 1 to 6 carbon atoms, and may be straight, branched or cyclic. Examples include
10 methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert-butyl, n-pentyl, isopentyl, hexyl, nonyl, decyl, dodecyl, tridecyl, cyclopentyl, and cyclohexyl.

 Where R^{204} and R^{205} , R^{205} and R^{206} , R^{204} and R^{206} , R^{204} with R^{205} and R^{206} , and R^{209} and R^{210} form rings, the rings preferably
15 have 1 to 20 carbon atoms, more preferably 1 to 8 carbon atoms, and most preferably 1 to 6 carbon atoms, and may have branching alkyl groups of 1 to 6 carbon atoms, and especially 1 to 4 carbon atoms.

 X, Y, and Z are each integers from 0 to 20, preferably from 1 to 10, and more preferably from 1 to 8.

20 Illustrative examples of the compounds of formulas (94) and (95) include tris(2-(methoxymethoxy)ethyl)amine, tris(2-(methoxyethoxy)ethyl)amine, tris[2-((2-methoxyethoxy)methoxy)ethyl]amine, tris(2-(2-methoxyethoxy)-ethyl)amine, tris(2-(1-methoxyethoxy)ethyl)amine, tris(2-(1-ethoxyethoxy)ethyl)amine, tris(2-(1-ethoxypropoxy)-ethyl)amine, tris[2-((2-hydroxyethoxy)ethoxy)ethyl]amine, 4,7,13,16,21,24-hexaoxa-1,10-diazabicyclo[8.8.8]hexacosane, 4,7,13,18-tetraoxa-1,10-diazabicyclo[8.5.5]eicosane, 1,4,10,13-tetraoxa-7,16-diazabicyclooctadecane, 1-aza-12-
25 crown-4, 1-aza-15-crown-5, and 1-aza-18-crown-6. Especially preferred basic compounds are tertiary amines, aniline derivatives, pyrrolidine derivatives, pyridine derivatives, quinoline derivatives, amino acid derivatives, hydroxyl group-bearing nitrogenous compounds, hydroxyphenyl group-
30 bearing nitrogenous compounds, alcoholic nitrogenous compounds, amide derivatives, imide derivatives, tris(2-(methoxymethoxy)ethyl)amine, tris(2-(2-methoxyethoxy)-

ethylamine, tris[2-((2-methoxyethoxy)methyl)ethyl]amine, and 1-aza-15-crown-5.

5 The above-described basic compound may be used singly or in combinations of two or more thereof, and is preferably formulated in an amount of 0.01 to 2 parts by weight, and especially 0.01 to 1 part by weight, per 100 parts by weight of all the base resins. At less than 0.01 part, the desired effects of the basic compound would not be apparent, while the use of more than 2 parts would result in too low a
10 sensitivity.

The resist composition of the invention may include optional ingredients, typically a surfactant which is commonly used for improving the coating characteristics. Optional ingredients may be added in conventional amounts so
15 long as this does not compromise the objects of the invention.

Nonionic surfactants are preferred, examples of which include perfluoroalkylpolyoxyethylene ethanols, fluorinated alkyl esters, perfluoroalkylamine oxides, and fluorinated
20 organosiloxane compounds. Useful surfactants are commercially available under the trade names Florade FC-430 and FC-431 from Sumitomo 3M Co., Ltd., Surflon S-141, S-145, S-381 and S-383 from Asahi Glass Co., Ltd., Unidyne DS-401, DS-403 and DS-451 from Daikin Industry Co., Ltd., Megaface
25 F-8151, F-171, F-172, F-173 and F-177 from Dai-Nippon Ink & Chemicals, Inc., and X-70-092 and X-70-093 from Shin-Etsu Chemical Co., Ltd. Preferred surfactants are Florade FC-430 from Sumitomo 3M K.K. and X-70-093 from Shin-Etsu Chemical Co., Ltd.

30 Pattern formation using the resist composition of the invention may be carried out by a known lithographic technique. For example, the resist composition is applied onto an organic film on a substrate such as a novolac film of about 0.1 to 10.0 μm thick on a silicon wafer by spin
35 coating or the like to form a resist film having a thickness of 0.1 to 1.0 μm , which is then pre-baked on a hot plate at 60 to 200°C for 10 seconds to 10 minutes, and preferably at

80 to 150°C for 30 seconds to 5 minutes. A patterning mask having the desired pattern is then placed over the resist film, and the film is exposed through the mask to an electron beam or high-energy radiation having a wavelength of up to 300 nm such as deep-UV, an excimer laser, or x-rays in a dose of about 1 to 200 mJ/cm², and preferably about 10 to 100 mJ/cm², then post-exposure baked (PEB) on a hot plate at 60 to 150°C for 10 seconds to 5 minutes, and preferably at 80 to 130°C for 30 seconds to 3 minutes. Development is then carried out using as the developer an aqueous alkali solution, such as a 0.1 to 5% (preferably 2 to 3%) aqueous solution of tetramethylammonium hydroxide (TMAH), this being done by a conventional method such as dipping, puddling, or spraying for a period of 10 seconds to 3 minutes, and preferably 30 seconds to 2 minutes. These steps result in the formation of the desired pattern on the substrate. Of the various types of high-energy radiation that may be used, the resist composition of the invention is best suited to micropattern formation with, in particular, deep-UV rays and excimer laser light having a wavelength of 254 to 120 nm, especially KrF excimer laser of 248 nm or ArF excimer laser of 193 nm, x-rays, and an electron beam. The desired pattern may not be obtainable outside the upper and lower limits of the above range.

In the developing step, the exposed area of the resist film is dissolved away until the underlying organic film is exposed. Then the exposed area of the organic film is conventionally processed with an oxygen plasma generated by a dry etching apparatus.

The resist composition comprising the polymer of the invention as a base resin is sensitive to high-energy radiation and has excellent sensitivity and resolution at a wavelength of less than 300 nm, and high resistance to oxygen plasma etching. Because of these advantages, the resist composition is suited for bi-layer resist and easily forms a finely defined pattern having sidewalls

perpendicular to the substrate. The resist composition lends itself to micropatterning for the fabrication of VLSIs.

EXAMPLE

5 Synthesis Examples and Examples are given below together with Comparative Examples for further illustrating the invention although the invention is not limited thereby. The abbreviations used have the following meaning, THF for tetrahydrofuran, Me for methyl, Et for ethyl, NMR for
10 nuclear magnetic resonance, Mw for weight average molecular weight, and Mn for number average molecular weight.

Silicon-containing monomers were synthesized according to the following procedures.

15 Synthesis Example 1-1: Synthesis of Monomer 1

A flask was charged with 36.5 g of magnesium and 350 ml of THF, to which a solution of 184 g of chloromethyltrimethylsilane diluted with 250 ml of THF was added dropwise at 50°C. The addition was followed by one hour of
20 stirring at 65°C, after which 66.1 g of acetaldehyde was added dropwise below 20°C. After one hour of stirring at room temperature, an aqueous solution of ammonium chloride was added for hydrolysis. Ordinary post-treatments yielded 158.7 g (yield 70%) of 1-trimethylsilyl-2-propanol.

25 In 500 ml of methylene chloride was dissolved 119.8 g of 1-trimethylsilyl-2-propanol. To the solution under ice cooling, 91.6 g of triethylamine was added dropwise, and 113.5 g of methacryloyl chloride then added dropwise. The solution was stirred for 5 hours at room temperature. Water
30 was added to the reaction mixture, followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 135.9 g (yield 75%) of 1-trimethylsilyl-2-propyl methacrylate (Monomer 1).

Boiling point: 75-77°C/1.33x10³ Pa

¹H-NMR (270 MHz, CDCl₃) σ : 0.03 (s, 9H), 0.87-1.14 (m, 2H), 1.28 (d, 3H), 1.92 (s, 3H), 5.04-5.16 (m, 1H), 5.51 (m, 1H), 6.05 (m, 1H)

IR: 2956, 2898, 1716, 1637, 1317, 1295, 1251, 1168, 1132, 1124, 863, 838 cm⁻¹

Synthesis Example 1-2: Synthesis of Monomer 2

As in Synthesis Example 1-1, 1-trimethylsilyl-2-propyl 5-norbornene-2-carboxylate (Monomer 2) was synthesized.

Synthesis Example 1-3: Synthesis of Monomer 3

As in Synthesis Example 1-1, 1-trimethylsilyl-2-propyl 8-tetracyclo[4.4.0.1^{2,5}.1^{7,10}]dodecene-3-carboxylate (Monomer 3) was synthesized.

Synthesis Example 1-4: Synthesis of Monomer 4

As in Synthesis Example 1-1, p-(1-trimethylsilyl-2-propoxy)styrene (Monomer 4) was synthesized.

Synthesis Example 1-5: Synthesis of Monomer 5

A flask was charged with 27.9 g of magnesium and 250 ml of THF, to which a solution of 135 g of chloromethyl-trimethylsilane diluted with 150 ml of THF was added dropwise at 50°C. The addition was followed by one hour of stirring at 65°C, after which 98.1 g of cyclohexanone was added dropwise below 20°C. After one hour of stirring at room temperature, an aqueous solution of ammonium chloride was added for hydrolysis. This was followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 141.6 g (yield 76%) of 1-trimethylsilylmethylcyclohexanol.

Boiling point: 60-62°C/66.6 Pa

¹H-NMR (270 MHz, CDCl₃) σ : 0.06 (s, 9H), 0.95 (s, 2H), 1.24 (s, 2H), 1.43-1.59 (m, 10H)

IR: 3471, 2933, 2859, 1448, 1247, 968, 948, 863, 838
cm⁻¹

In 50 ml of methylene chloride was dissolved 10.0 g of
1-trimethylsilylmethylcyclohexanol. To the solution under
ice cooling, 7.8 g of methacryloyl chloride was added
dropwise, and 9.8 g of triethylamine then added dropwise.
The solution was stirred for 20 hours at room temperature.
Water was added to the reaction mixture, followed by
ordinary post-treatments. Upon vacuum distillation, there
was obtained 10.8 g (yield 79%) of 1-trimethylsilylmethyl-
cyclohexyl methacrylate (Monomer 5).

Boiling point: 78-81°C/53.3 Pa

¹H-NMR (270 MHz, CDCl₃) δ : 0.16 (s, 9H), 1.12-1.65 (m,
10H), 1.91 (t, 3H), 2.25-2.32 (m, 2H), 5.48 (m, 1H), 6.03 (m,
1H)

IR: 2933, 2859, 1712, 1637, 1326, 1309, 1249, 1178,
1159, 1126, 858, 840 cm⁻¹

Synthesis Example 1-6: Synthesis of Monomer 6

As in Synthesis Example 1-5, 1-trimethylsilylmethyl-
cyclohexyl 5-norbornene-2-carboxylate (Monomer 6) was
synthesized.

Synthesis Example 1-7: Synthesis of Monomer 7

As in Synthesis Example 1-5, 1-trimethylsilylmethyl-
cyclohexyl p-vinylphenoxyacetate (Monomer 7) was synthesized.

Synthesis Example 1-8: Synthesis of Monomer 8

A flask was charged with 14.6 g of magnesium and 120
ml of THF, to which a solution of 67.5 g of chloromethyl-
trimethylsilane diluted with 70 ml of THF was added dropwise
at 50°C. The addition was followed by one hour of stirring
at 65°C, after which 42.1 g of cyclopentanone was added
dropwise below 20°C. After one hour of stirring at room
temperature, an aqueous solution of ammonium chloride was
added for hydrolysis. This was followed by ordinary post-

treatments. Upon vacuum distillation, there was obtained 70.6 g (yield 82%) of 1-trimethylsilylmethylcyclopentanol.

In 160 ml of methylene chloride was dissolved 34.5 g of 1-trimethylsilylmethylcyclopentanol. To the solution under ice cooling, 29.3 g of methacryloyl chloride was added dropwise, and 30.4 g of triethylamine then added dropwise. The solution was stirred for 20 hours at room temperature. Water was added to the reaction mixture, followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 39.9 g (yield 83%) of 1-trimethylsilylmethylcyclopentyl methacrylate (Monomer 8).

Synthesis Example 1-9: Synthesis of Monomer 9

As in Synthesis Example 1-8, 1-trimethylsilylmethylcyclopentyl 5-norbornene-2-carboxylate (Monomer 9) was synthesized.

Synthesis Example 1-10: Synthesis of Monomer 10

A flask was charged with 300 ml of a THF solution of 1M methylmagnesium chloride, to which 17.4 g of ethyl 3-trimethylsilylpropanoate was added dropwise below 50°C. The solution was stirred for one hour at room temperature, after which an aqueous solution of ammonium chloride was added for hydrolysis. This was followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 14.1 g (yield 88%) of 2-methyl-4-trimethylsilyl-2-butanol.

Boiling point: 85-88°C/3.33x10³ Pa

¹H-NMR (270 MHz, CDCl₃) σ : 0.00 (s, 9H), 0.45-0.51 (m, 2H), 1.18 (s, 6H), 1.36-1.44 (m, 3H)

IR: 3378, 2954, 2921, 2900, 1376, 1247, 1186, 904, 885, 863, 835 cm⁻¹

In 50 ml of methylene chloride was dissolved 9.5 g of 2-methyl-4-trimethylsilyl-2-butanol. To the solution under ice cooling, 9.8 g of methacryloyl chloride was added dropwise, and 12.0 g of triethylamine then added dropwise. The solution was stirred for 20 hours at room temperature.

Water was added to the reaction mixture, followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 11.2 g (yield 83%) of 2-methyl-4-trimethylsilyl-2-butyl methacrylate (Monomer 10).

5 Boiling point: 71-73°C/3.33x10² Pa

¹H-NMR (270 MHz, CDCl₃) σ : 0.00 (s, 9H), 0.44-0.51 (m, 2H), 1.45 (s, 6H), 1.68-1.75 (m, 2H), 1.89 (s, 3H), 5.45 (m, 1H), 5.98 (m, 1H)

IR: 2954, 2929, 1714, 1639, 1332, 1302, 1249, 1168,
10 1147, 1126, 862, 835 cm⁻¹

Synthesis Example 1-11: Synthesis of Monomer 11

As in Synthesis Example 1-10, 2-methyl-4-trimethylsilyl-2-butyl 5-norbornene-2-carboxylate (Monomer 11) was synthesized.
15

Synthesis Example 1-12: Synthesis of Monomer 12

A flask was charged with 9.82 g of magnesium and 150 ml of THF, to which a solution of 43.5 g of 1,4-dibromobutane diluted with 50 ml of THF was added dropwise at 50°C.
20 The solution was stirred for one hour at 65°C, after which 23.5 g of ethyl 3-trimethylsilylpropionate was added dropwise below 50°C. The solution was stirred for one hour at room temperature, after which an aqueous solution of
25 ammonium chloride was added for hydrolysis. This was followed by ordinary post-treatments. Upon vacuum distillation, there was obtained 23.6 g (yield 94%) of 1-(2-trimethylsilylethyl)cyclopentanol.

Boiling point: 71-72°C/53.3 Pa

30 ¹H-NMR (270 MHz, CDCl₃) σ : 0.00 (s, 9H), 0.50-0.57 (m, 2H), 1.29 (s, 1H), 1.48-1.67 (m, 8H), 1.72-1.87 (m, 2H)

IR: 3372, 2954, 1247, 1245, 991, 896, 862, 836 cm⁻¹

In 60 ml of methylene chloride was dissolved 12.0 g of 1-(2-trimethylsilylethyl)cyclopentanol. To the solution
35 under ice cooling, 11.8 g of methacryloyl chloride was added

dropwise, and 14.3 g of triethylamine then added dropwise. The solution was stirred for 20 hours at room temperature. Water was added to the reaction mixture, followed by ordinary post-treatments. Upon vacuum distillation, there
5 was obtained 14.0 g (yield 85%) of 1-(2-trimethylsilylethyl)cyclopentyl methacrylate (Monomer 12).

Boiling point: 74-75°C/40.0 Pa

¹H-NMR (270 MHz, CDCl₃) σ : 0.16 (s, 9H), 1.12-1.65 (m, 10H), 1.91 (t, 3H), 2.25-2.32 (m, 2H), 5.48 (m, 1H), 6.03 (m,
10 1H)

IR: 2933, 2859, 1712, 1637, 1326, 1309, 1249, 1178, 1159, 1126, 858, 840 cm⁻¹

Synthesis Example 1-13: Synthesis of Monomer 13

15 As in Synthesis Example 1-12, 1-(2-trimethylsilylethyl)cyclopentyl 8-tetracyclo[4.4.0.1^{2,5}.1^{7,10}]dodecene-3-carboxylate (Monomer 13) was synthesized.

20 The following monomers (Monomers 14 to 20) were synthesized by analogous reaction or well-known reaction procedures.

Synthesis Example 1-14: Synthesis of Monomer 14

25 1-trimethylsilylmethyl-4,4-dimethyl-4-silacyclohexyl methacrylate

Synthesis Example 1-15: Synthesis of Monomer 15

30 p-(1-trimethylsilylmethyl-4,4-dimethyl-4-silacyclohexyloxy)styrene

Synthesis Example 1-16: Synthesis of Monomer 16

1-trimethylsilylmethyl-3,3,5,5-tetramethyl-3,5-disilacyclohexyl methacrylate

35 Synthesis Example 1-17: Synthesis of Monomer 17

1-trimethylsilylmethyl-3,3-dimethyl-3-silacyclopentyl p-vinylphenoxyacetate

Synthesis Example 1-18: Synthesis of Monomer 18


1-trimethylsilylmethyl-3,3-dimethyl-3-silacyclohexyl
acrylate

5 Synthesis Example 1-19: Synthesis of Monomer 19


1-trimethylsilylmethyl-2,2,4,4,6,6-hexamethyl-2,4,6-
trisilacyclohexyl 5-norbornene-2-carboxylate

Synthesis Example 1-20: Synthesis of Monomer 20


10 1-(2-triethylsilylethyl)cyclopentyl 8-tetracyclo-
[4.4.0.1^{2,5}.1^{7,10}]dodecene-3-carboxylate




Monomer 1




Monomer 2




Monomer 3




Monomer 4




Monomer 5




Monomer 6




Monomer 7




Monomer 8




Monomer 9




Monomer 10




Monomer 11




Monomer 12




Monomer 13



Monomer 14



Monomer 15



A silicon-containing polymer was synthesized according to the following procedure.


Synthesis Example 2-1: Synthesis of Polymer 1

In 100 ml of THF were dissolved 12.0 g of Monomer 1 and 6.8 g of 2-oxo-2,3,4,5-tetrahydrofuran-3-yl methacrylate. Then 1.6 g of 2,2'-azobisisobutyronitrile was added thereto. The solution was stirred for 15 hours at 60°C and then added dropwise to 2 liters of n-hexane. The resulting solids were collected by filtration, washed with 1 liter of n-hexane, and vacuum dried at 40°C for 6 hours, obtaining 11.8 g of a polymer shown below as Polymer 1. The yield was 63%. On GPC analysis using a polystyrene standard, it had a M_w of 10,000 and a polydispersity (M_w/M_n) of 1.80.

Polymers 2 to 23 were synthesized by similar or well-known procedures.


Polymer 1

$c = 0.6$ $d = 0.4$
 $M_w = 10000$ $M_w/M_n = 1.80$




Polymer 2

$c = 0.5$ $d = 0.5$
 $M_w = 6000$ $M_w/M_n = 1.75$




Polymer 3

$c = 0.5$ $d = 0.5$
 $M_w = 5000$ $M_w/M_n = 1.65$




Polymer 4

$c = 0.4$ $d = 0.6$
 $M_w = 12000$ $M_w/M_n = 1.80$




Polymer 5

$c = 0.6$ $d = 0.4$
 $M_w = 10500$ $M_w/M_n = 1.85$




Polymer 6

$c = 0.5$ $d = 0.5$
 $M_w = 6050$ $M_w/M_n = 1.80$




Polymer 7

$c = 0.3$ $d = 0.7$
 $M_w = 10500$ $M_w/M_n = 1.80$




Polymer 8

$c = 0.6$ $d = 0.4$
 $M_w = 10800$ $M_w/M_n = 1.65$




Polymer 9

$c = 0.5$ $d = 0.5$
 $M_w = 8000$ $M_w/M_n = 1.85$




Polymer 10

$c = 0.6$ $d = 0.4$
 $M_w = 12500$ $M_w/M_n = 1.65$




Polymer 11

$c = 0.5$ $d = 0.5$
 $M_w = 8000$ $M_w/M_n = 1.83$




Polymer 12

$c = 0.6$ $d = 0.4$
 $M_w = 10500$ $M_w/M_n = 1.80$




Polymer 13

$c = 0.5$ $d = 0.5$
 $M_w = 5000$ $M_w/M_n = 1.82$




Polymer 14

$c = 0.6$ $d = 0.4$
 $M_w = 11000$ $M_w/M_n = 1.75$




Polymer 15

$c = 0.3$ $d = 0.7$
 $M_w = 12000$ $M_w/M_n = 1.81$




Polymer 16

$c = 0.6$ $d = 0.4$
 $M_w = 10400$ $M_w/M_n = 1.80$




Polymer 17

$c = 0.3$ $d = 0.7$
 $M_w = 11200$ $M_w/M_n = 1.86$




Polymer 18

$c = 0.6$ $d = 0.4$
 $M_w = 11300$ $M_w/M_n = 1.68$




Polymer 19

$c = 0.5$ $d = 0.5$
 $M_w = 8600$ $M_w/M_n = 1.82$




Polymer 20

$c = 0.5$ $d = 0.5$
 $M_w = 6200$ $M_w/M_n = 1.76$




Polymer 21

$c = 0.6$ $d = 0.4$
 $M_w = 10200$ $M_w/M_n = 1.65$




Polymer 22

$c = 0.6$ $d = 0.3$ $e = 0.1$
 $M_w = 8700$ $M_w/M_n = 1.82$



Polymer 23


c = 0.6 d = 0.3 e = 0.1
Mw = 8200 Mw/Mn = 1.80




Resist compositions within the scope of the invention were examined for resolution upon KrF excimer laser exposure.

5 Examples 1-28: Resist resolution


10 Resist solutions were prepared by dissolving Polymers 1 to 23 of the above formulae as the base resin, a photoacid generator (designated as PAG1 or 2), a basic compound (TBA, TEA or TMMEA), and a dissolution rate inhibitor (designated as DRI1 or 2) in PGMEA containing 0.01% by weight of surfactant Florade FC-430 (Sumitomo 3M), followed by filtration through a Teflon filter (pore diameter 0.10 μ m).




PAG1



PAG2



DRI1



DRI2

TBA: tributylamine

TEA: triethanolamine

TMMEA: trismethoxymethoxyethylamine

PGMEA: propylene glycol monomethyl ether acetate

5 On silicon wafers, lower resist films of 0.5 μm thick were formed by applying novolac resist material OFPR-800 (Tokyo Ohka Kogyo Co., Ltd.) and heating at 300°C for 5 minutes for curing. Antireflection films of 55 nm thick were formed thereon by spin coating DUV-30 (Brewer Science) and baking at 100°C for 30 seconds and then at 200°C for 60 seconds.

15 On the cured DUV-30/novolac resist/silicon wafer, the resist solutions were spin coated, then baked on a hot plate at 100°C for 90 seconds to give resist films of 0.2 μm thick. Using a KrF excimer laser stepper (Nikon Corporation, NA 0.60), the resist films were exposed. The resist films were baked (PEB) at 110°C for 90 seconds and then developed with a 2.38% aqueous solution of tetramethylammonium hydroxide, obtaining positive patterns.

20 The sensitivity of the resist was the exposure dose (mJ/cm^2) which provided a 1:1 line-to-space ratio in a 0.20 μm line-and-space pattern. The resolution of the resist was the minimum line width (μm) of the lines and spaces that separated at this dose.

25 Using a parallel plate sputter etching apparatus TE-8500 by Tokyo Electron Co., Ltd., the resist films were etched with an etchant, oxygen gas under the following conditions.

30 Oxygen gas flow rate: 0.05 l/min

Gas pressure: 1.3 Pa

RF power: 50 W

DC bias: 450 V

35 The lower resist film was etched at a rate of 150 nm/min whereas the inventive resist film was etched at a rate of 15 nm/min. After 2 minutes of etching, those portions of the lower resist film which were not covered

with the inventive resist film disappeared completely,
leaving a bi-layer resist pattern having a thickness of 0.5
 μm .

The evaluation results of the resists are shown in

5 Table 1.

5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214
2215
2216
2217
2218
2219
2220
2221
222

Table 1

Example	Resin (pbw)	Photoacid generator (pbw)	Basic compound (pbw)	Dissolution rate inhibitor (pbw)	Solvent (pbw)	Sensitivity (mJ/cm ²)	Resolution (μm)
1	Polymer1 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	26	0.16
2	Polymer2 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	20	0.17
3	Polymer3 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	28	0.17
4	Polymer4 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	20	0.17
5	Polymer5 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	30	0.17
6	Polymer6 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	27	0.16
7	Polymer7 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	20	0.17
8	Polymer8 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	28	0.17
9	Polymer9 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	30	0.18
10	Polymer10 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	32	0.18
11	Polymer11 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	35	0.19
12	Polymer12 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	28	0.17
13	Polymer13 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	32	0.18
14	Polymer14 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	26	0.16
15	Polymer15 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	19	0.18
16	Polymer16 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	24	0.16
17	Polymer17 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	17	0.17
18	Polymer18 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	26	0.16
19	Polymer19 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	24	0.17
20	Polymer20 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	29	0.18
21	Polymer21 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	27	0.16
22	Polymer22 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	25	0.16
23	Polymer23 (80)	PAG1 (2)	TBA (0.1)		PGMEA (1000)	29	0.17
24	Polymer1 (80)	PAG2 (2)	TBA (0.1)		PGMEA (1000)	17	0.16
25	Polymer1 (70)	PAG1 (1)	TBA (0.1)	DRI1 (10)	PGMEA (1000)	24	0.16
26	Polymer1 (70)	PAG1 (1)	TBA (0.1)	DRI2 (10)	PGMEA (1000)	23	0.16
27	Polymer1 (80)	PAG1 (1)	TEA (0.1)		PGMEA (1000)	28	0.16
28	Polymer1 (80)	PAG1 (1)	TMMEA (0.2)		PGMEA (1000)	30	0.16

